

JUPITER DISPLAY

PRODUCT: ST-117

FEATURES / APPLICATIONS:

- Special tight structure makes it with high opacity even at a much lighter weight compared with other display textile fabric
- Truly wrinkle free, can recover quickly after folded, makes it easy for transportation
- Soft, smooth, has good textile hand feel
- Can be coated for dye-sub direct, dye-sub transfer printing, also with good printing image by latex inks

MATERIAL DETAILS

PROPERTIES	TEST METHOD	METRIC	IMPERIAL
Total Weight	DIN EN ISO 2286-2	210g/sq.m	6.1oz/sq.yd.
Base Fabric	DIN 60001	Polyester	Polyester
Yarn Dtex	DIN EN ISO 2060	83x55x55 dtex	75x50x50 denier
Weave Method	N/A	Warp-knitted	3 bar
White Point (CIE/D65)	CIE86/ASTME313-00(D65/10,SCI)	≥133	
Shrinkage	N/A	≤2% (190°C , 1min)	
Obscuring ratio	X-Rite 341C	52%	
Flame Resistance	/	DIN 4102-1-B1 , NFPA 701	
Recommend fixation	N/A	190°C-210°C , 1-2min	
Transfer temperature	N/A	190°C-210°C , 1-2min	
Yellowing temperature	SUPRKC REX-C400	230°C	
Width	N/A	Max 320cm	126"
Standard Length	N/A	50m	55yd

INK PRINTABILITY

Solvent	Eco Solvent	UV	Latex
			<input type="checkbox"/>
Screen Printing	Dye Transfer	Dye Direct	
	<input type="checkbox"/>	<input type="checkbox"/>	

NOTE: All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty

**Soyang Technologies Co.,
(Soyang Headquarters)**

West 19th FL, Yongtong
Information plaza, No. 141
Huancheng Bei Road, Hangzhou

www.soyang.net

P. 0086-571-28918690

F. 0086-571-28918695

Soyang Haining Factory

No.36 Jinniu Road,Jianshan District,Haining City, Zhejiang PR,China.

Soyang Hangzhou Factory

No,1199 Gongyuan Xi Rd, Fuyang, Hangzhou City, Zhejiang, PR,
China

Soyang Europe Ltd

Calder House Metcalf Drive
Altham Industrial estate
Altham Lancashire BB5 5TU UK

www.soyang.co.uk

P. 0044 (0) 161 765 3400

F. 0044 (0) 1282 772982