



PRIME DISPLAY FABRIC CLASSIC

PRODUCT: ST-117T/ST-117D

FEATURES:

- Special tight structure makes it with high opacity even at a much lighter weight compared with other display textile fabric;
- Truly wrinkle free, can recover quickly after folded, makes it easy for transportation;
- Soft, smooth, has good textile hand feel;
- Can be coated for Dye-sub direct, Dye-sub transfer printing, also with good printing images by Latex inks.

APPLICATIONS:

-Display Pop-up Backdrops

MATERIAL DETAILS

MINITERINAL DE INICO					
PROPERTIES	TEST METHOD	METRIC	IMPERIAL		
Total Weight	DIN EN ISO 2286-2, ASTM D751	220 g/sq.m	6.4 oz/sq.yd		
Base Fabric	DIN 60001, ASTM D7641	Polyester	Polyester		
Weave Method	N/A	Warp-knitted 3 bar			
Shrinkage	N/A	≤2% (210°C, 30s)			
Shielding Rate	ANSI PH2.19, ISO 5/2	(50±4)%			
Flame Resistance)IN 4102-1-B1, NFPA 701 Test1, NF P92 M1	DIN 4102-1-B1, NFPA 701 Test1, NF P92 M1			
Recommend Fixation Temperature	N/A	190°C-210°C, 1-2min			
Yellowing Temperature	SUPRKC REX-C400, 30s	≥210°C			
Width Available	DIN EN ISO 3759, ASTM D751-	Max 320cm	126"		
Standard Length	DIN EN ISO 3759, ASTM D751-	50m	55yds		

INK PRINTABILITY

Solvent	Eco Solvent	υv	Latex
Screen Printing	Dye Transfer	Dye Direct	

NOTE: It is normal that the weight of most products will have an average fluctuation of 5%. All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty.

Soyang Technologies Co.,	Soyang Technical Textile (Zhejiang) Co., Ltd	Soyang Europe Ltd		
Ltd (Soyang Headquarters)				
West 19th FL, Yongtong Information	No. 36 Jinniu Road, Jianshan District, Haining City, Zhejiang PR, China	Calder House Metcalf Drive		
plaza, No. 141 Huancheng Bei Road, Hangzhou City, Zhejiang PR.,		Altham Industrial estate Altham Lancashire BB5 5TU UK		
China	Hangzhou Soyang Flexible Material Co., Ltd			
www.soyang.net	Hangzhou Soyang Piexible Material Co., Ltu	www.soyang.co.uk		
P. 0086-571-28918697		P. 0044 (0) 161 765 3400		
F. 0086-571-28918695	No,1199 Gongyuan Xi Rd, Fuyang, Hangzhou City, Zhejiang, PR, China	F. 0044 (0) 1282 772982		