



Product: 350FRX FlagSuperb

support cloth:

Faserstoff des Trägergewebes
tissue
natura del supporto

100% Polyester



design:

Bindung
armure
tipo di tessitura

knitted fabric

total weight [g/sqm]:

Flächengewicht
poids total
peso total

110 g/m²

width [cm]:

Breite
largeur
larghezza

155, 255, 310

certified according:

Zertifizierung
remarques
rimarchi

DIN 4102-01, B1

Technische Änderungen behalten wir uns vor. Werte ohne Toleranzangaben sind Nennwerte mit einer Toleranz von +/-10%
Angaben entsprechen dem heutigen Stand ohne Rechtsverbindliche Aussage.
Technical data corresponds with our latest knowledge and is offered without liability.



Product: 3118FRX BeachFlag

support cloth:

Faserstoff des Trägergewebes
tissue
natura del supporto

100% Polyester



design:

Bindung
armure
tipo di tessitura

knitted fabric

total weight [g/sqm]:

Flächengewicht
poids total
peso total

115 g/m²

width [cm]:

Breite
largeur
larghezza

155, 255, 310, 320 cm

certified according:

Zertifizierung
remarques
rimarchi

DIN 4102-01, B1

Technische Änderungen behalten wir uns vor. Werte ohne Toleranzangaben sind Nennwerte mit einer Toleranz von +/-10%
Angaben entsprechen dem heutigen Stand ohne Rechtsverbindliche Aussage.
Technical data corresponds with our latest knowledge and is offered without liability.



PRODUCT REFERENCE



ALTIMIS

CHARACTERISTICS

BASE CLOTH	100% Polyester with 100% recycled yarn
WIDTH AVAILABLE	63 inch / 126 inch 160 cm / 320 cm
WEIGHT	3,69 oz. /sq. yd 130 g/m²
THICKNESS	0,13 mm
FIRE CLASSIFICATION	(M1 & B1 in process)
TENSILE STRENGTH	Warp/Weft : 42 daN / 78 daN CH/TR : 42 daN / 78 daN
PRINTING	Water based & UV-curable inks on the polyester side. Care to be taken in cold temperatures after UV printing (printing side rolled inside)
FIELD OF APPLICATION	An alternative that respects of the environnement in the soft signage print market , we recommend this coated textile with optimum light diffusion for high impact graphics for S.E.G , backlit light boxes, trade show & events.
CERTIFICATION	évalué par AFNOR CERTIFICATION Confirmé

EDITION : 03/05/2019 / REF : DECOPRINT_FT_ALTIMIS / CONCEPTION ET REALISATION : SERVICE COMMUNICATION SENFA

All details are nominal values and are subject to change within usual tolerance (+/- 10 %). The information provided in this document is based on current knowledge and expertise. They do not exempt a manufacturer/processor from carrying out their own tests and trials as their in-house handling and manufacturing processes can have a significant range of influences on outcomes. Application, utilisation and processing of products is taking place outside of our control and are therefore the sole responsibility of the manufacturer/processor.

POPULAR FLAG

PRODUCT: ST-110T/ST-110D

FEATURES

- 100% polyester texturized warp-knitted fabric, semi-matte
- It makes an excellent double penetration effect after Dye-sub printing

APPLICATIONS:

- Flags



MATERIAL DETAILS

PROPERTIES	TEST METHOD	METRIC	IMPERIAL
Total Weight	DIN EN ISO 2286-2, ASTM D751	110 g/sq.m	3.2 oz/sq.yd
Base Fabric	DIN 60001, ASTM D7641	Polyester	Polyester
Weave Method	N/A	Warp-knitted 3 bar	
Shrinkage	N/A	≤2% (210°C, 30s)	
Flame Resistance	DIN 4102-1-B1, NFPA 701 Test1	DIN 4102-1-B1, NFPA 701 Test1	
Recommend Fixation Temperature	N/A	190°C-210°C, 1-2min	
Yellowing Temperature	SUPRKC REX-C400, 30s	≥210°C	
Width Available	DIN EN ISO 3759, ASTM D751-2009	Max 320cm	126"
Standard Length	DIN EN ISO 3759, ASTM D751-2009	100m	110yds

INK PRINTABILITY

Solvent	Eco Solvent	UV	Latex
Screen Printing	Dye Transfer	Dye Direct	
	☐	☐	

NOTE: It is normal that the weight of most products will have an average fluctuation of 5%. All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty.

Soyang Technologies Co., Ltd (Soyang)
 West 19th FL, Yongtong Information plaza, No. 141 Huancheng Bei Road, Hangzhou City, Zhejiang PR., China

www.soyang.net

P. 0086-571-28918697

F. 0086-571-28918695

Soyang Technical Textile (Zhejiang) Co., Ltd

No. 36 Jinniu Road, Jianshan District, Haining City, Zhejiang PR, China

Hangzhou Soyang Flexible Material Co., Ltd

No,1199 Gongyuan Xi Rd, Fuyang, Hangzhou City, Zhejiang, PR, China

Soyang Europe Ltd

Calder House Metcalf Drive
 Altham Industrial estate
 Altham Lancashire BB5 5TU UK

www.soyang.co.uk

P. 0044 (0) 161 765 3400

F. 0044 (0) 1282 772982

RECYCLE POPULAR FLAG

PRODUCT: ST-110(R)T/ST-110(R)D

FEATURES

- 100% polyester texturized warp-knitted fabric by using recycled yarns, environmental friendly
- It makes an excellent double penetration effect after Dye-sub printing

APPLICATIONS:

- Flags



MATERIAL DETAILS

PROPERTIES	TEST METHOD	METRIC	IMPERIAL
Total Weight	DIN EN ISO 2286-2, ASTM D751	110 g/sq.m	3.2 oz/sq.yd
Base Fabric	DIN 60001, ASTM D7641	Polyester	Polyester
Weave Method	N/A	Warp-knitted 3 bar	
Shrinkage	N/A	≤2% (210°C, 30s)	
Flame Resistance	DIN 4102-1-B1, NFPA 701 Test1	DIN 4102-1-B1, NFPA 701 Test1	
Recommend Fixation Temperature	N/A	190°C-210°C, 1-2min	
Yellowing Temperature	SUPRKC REX-C400, 30s	≥210°C	
Width Available	DIN EN ISO 3759, ASTM D751-	Max 320cm	126"
Standard Length	DIN EN ISO 3759, ASTM D751-	100m	110yds

INK PRINTABILITY

Solvent	Eco Solvent	UV	Latex
Screen Printing	Dye Transfer	Dye Direct	
	☐	☐	

NOTE: It is normal that the weight of most products will have an average fluctuation of 5%. All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty.

Soyang Technologies Co., Ltd (Soyang)
 West 19th FL, Yongtong Information plaza, No. 141 Huancheng Bei Road, Hangzhou City, Zhejiang PR., China

www.soyang.net

P. 0086-571-28918697

F. 0086-571-28918695

Soyang Technical Textile (Zhejiang) Co., Ltd

No. 36 Jinniu Road, Jianshan District, Haining City, Zhejiang PR, China

Hangzhou Soyang Flexible Material Co., Ltd

No.1199 Gongyuan Xi Rd, Fuyang, Hangzhou City, Zhejiang, PR, China

Soyang Europe Ltd

Calder House Metcalf Drive
 Altham Industrial estate
 Altham Lancashire BB5 5TU UK

www.soyang.co.uk

P. 0044 (0) 161 765 3400

F. 0044 (0) 1282 772982

MESH FLAG

PRODUCT: ST-118T/ST-118D

FEATURES

- 100% polyester mesh, semi-glossy finish
- Good soft texture and double penetration effect

APPLICATIONS:

- Flags



MATERIAL DETAILS

PROPERTIES	TEST METHOD	METRIC	IMPERIAL
Total Weight	DIN EN ISO 2286-2, ASTM D751	115 g/sq.m	3.3 oz/sq.yd
Base Fabric	DIN 60001, ASTM D7641	Polyester	Polyester
Weave Method	N/A	Warp-knitted 3 bar	
Shrinkage	N/A	≤2% (210°C, 30s)	
Flame Resistance	DIN 4102-1-B1, NFPA 701 Test1	DIN 4102-1-B1, NFPA 701 Test1	
Recommend Fixation Temperature	N/A	190°C-210°C, 1-2min	
Yellowing Temperature	SUPRKC REX-C400, 30s	≥210°C	
Width Available	DIN EN ISO 3759, ASTM D751- 7744	Max 320cm	126"
Standard Length	DIN EN ISO 3759, ASTM D751- 7744	100m	110yds

INK PRINTABILITY

Solvent	Eco Solvent	UV	Latex
Screen Printing	Dye Transfer	Dye Direct	
	☐	☐	

NOTE: It is normal that the weight of most products will have an average fluctuation of 5%. All above information shall only used as a guide; buyers shall independently test and determine the products suitability. The mentioned data are average of test result and should not be used for the purpose of lawsuit or warranty.

Soyang Technologies Co., Ltd (Soyang Headquarters)
West 19th FL, Yongtong Information plaza, No. 141 Huancheng Bei Road, Hangzhou City, Zhejiang PR., China

www.soyang.net

P. 0086-571-28918690

F. 0086-571-28918695

Soyang Technical Textile (Zhejiang) Co., Ltd

No. 36 Jinniu Road, Jianshan District, Haining City, Zhejiang PR, China

Hangzhou Soyang Flexible Material Co., Ltd

No.1199 Gongyuan Xi Rd, Fuyang, Hangzhou City, Zhejiang, PR, China

Soyang Europe Ltd

Calder House Metcalf Drive
Altham Industrial estate
Altham Lancashire BB5 5TU UK

www.soyang.co.uk

P. 0044 (0) 161 765 3400

F. 0044 (0) 1282 772982